

## ANTIFOULING IN THE CHILEAN SALMON FARMING INDUSTRY



Sandra Bravo
Universidad Austral de Chile sbravo@uach.cl



Per Gunnar Kvenseth – Senior Consultant – Villa Salmon - Norway

Sandra Bravo, Ma. Teresa Silva & Claudia Lagos Universidad Austral de Chile – Puerto Montt - Chile



## **Chilean salmon Industry**

- Started in the beginning of 1980s
- Chile the second largest salmon producer since 1992
- 387.000 ton in 1996 (84% in region X)
- Only one company involved in organic salmon (2002 2005)
- One of the main technical problems at ongrowing in the sea is;
- FOULING (nets and equipment)
- Variations; seasonal, temp., salinity, tides, etc.
- Fouling can reduce water flow through nets by 40%
- Will have direct effect on fish health (reduces oxygen, increased fish waste and ammonia)
- Attached organisms can act as pathogenes agens



## Copper

- The only metal allowed in antifouling for fishfarming nets in Chile
- Copper is defined as an environmental toxin
- Copper can accumulate in algae, oysters, mussels and crabs
- The antifouling effect comes from slowly and constant "leakage" of copper – giving a zone around the tread (net) permanently surrounded by a thin layer of toxic solution.
- Effective at about 10-20 microgram copper/cm<sup>2</sup>/day



# Periods of protection against fouling in antifouling nets v/s without antifouling coating (net changing rate)

	Autumn - winter	Autumn - winter	Spring - summer	Spring - summer
Mesh size	With antifouling	Without antifouling	With antifouling	Without antifouling
Smolt	16-24 weeks	4-6 weeks	13-21 weeks	10-12 days
On-growing	16-32 weeks	4-7 weeks	17-26 weeks	15-20 days



## Methology

- Data collection (1999-2003)
- Questionary to seven companies selling antifouling paint in Chile
- Also questionary to 20 companies giving antifouling service (users)



## Results

Antifouling suppliers to the Chilean market during 1999-2003

Product	Characteristics	Saler	Producer	
1	solvent based			
Flexgard	waterbase	Aqua Cards	Flexabar Aquatech Co.	
Hempanet 7150 A	solvent based	Kupfer	Pinturas Hempel	
Norimp 2000	solvent based	Ceresita	Jotun-Henry Clark Ltda	
B 04464 Q	solvent based	Sherwin Williams	Sherwin Williams	
1 1 1	solvent based			
Aquasafe	waterbase	Equipos Industriales	Gjoco Industrier AS	
Netguard	solvent based			
Aquanet	waterbase	Bayer	Sten-Hansen Maling AS	
Netrex*	waterbase	Akva Chile	NetKem AS	



## Results

## Characteristics of antifouling paints used in Chile 1999-2003

Product	Solvents	Active Ingredient	Binder	Specific gravity (g/cm <sup>3</sup> )	Total Solids (%)	(%) Copper (oxid)
Aquasafe	xylol white spirit	copper oxide	natural gum resin	1,27	45	15-25
Aquasafe-W	water	copper oxide	acrylic / wax emulsion	1,27	54	15-30
Aqua-Net	water	copper oxide	Acrylic	1,34	42- 50	10-30
Net-Guard	white spirit xylol	copper oxide	sintetic resin	1,22	48-55	10-30
Norimp 2000	white spirit xylol	copper oxide	Colophony	1.2 – 1.4	57 <u>+</u> 2	10–20
Hempanet 7150 A	xylol white spirit	copper oxide	Colophony	1.35 ± 0.1	50	10-15
Flexgard	white spirit	copper oxide	natural gum resin	1.5ó – 1.56	67 ± 5	15-20
Flexgard	water	copper oxide		1.45 -1.49	55	10-15
B 04464 Q	white spirit	copper oxide	Colophony	1,2 <u>+</u> 0,02	59 <u>+</u> 2	7




### Results

- Total sales in 1999 1,760,000 litre
- With 20% Copper -> 460 tons of Copper
- 3,4% waterbased
- Total sales 2003 4,672,886 litre (+ 265,5%)
- With 20% Copper -> 1200 tons of Copper (Norway ab. 200 tons = 1/6)
- 11,4% waterbased



## Salmon production in Chile v/s antifouling used by the industry





#### **Discussion**

- Increase in use why?
  - increase in net cage size,
  - more open sites in use giving difficult service / net changing
- Quickly invation by fouling when antifouling (copper) in painted net is "used up" / leaching is over (seaweed, mollusks, mussels etc.)
- Low % of waterbased antifouling in use compared to the Europe industry



## Alternative solutions,

 Washers, brushers, high preassure disks, etc. Divers or surface operated. Not a good solution – lots of suspended materials causing gill problems for the salmon, environmental problems (organic loads?) and difficult to operate (exposed sites?)



#### Discussion-cont.

- Farms in Reg. X with no use of antifouling (experiments?) -> changing every 20 day in the summer every 2 month in the winter
- Such frequent net handling can cause escaping fish, stress, poor welfare and diseases if not done a suitable way
- Copper based paint will be banned in Chile asap an accaptable alternative is available (copper less hazardouse than TBT – 1/1000)
- Antifouling (with copper ?) not permitted in lakes in Chile
- Strict regulations for net washing and copper outlet to environment (max 1 mg/litre)






Project financed by Fondo de Investigacion Pesquera (FIP) of the 14 **Undersecretary of Fisheries – FIP 2003-28** 



## **Antifouling in the Norwegian Aquaculture industry**

- Dominated by coppercontaining antifouling ab 200 tons copper/year
- Industry goal to reduce this to 20 tons/year
- Increased use of paint without toxin (Netpolish, Net coating)
- Purpose to give a smooth sutface of the tread (easy to clean)
- and
- To pack the treads in the net closer together (more difficult for organisms to eatablish)
- Increasing use of unpainted nets and the use of cleaning high preassure disks (surface operated and divers operated) – development driven by organic farmers
- Increased use of "environmental nets" two nets attached to each other
   one in use one out of water sundried rain exposed
- The Norwegian use of CLEANERFISH reduces the need for antifouling paint – by grazing on the nets





# Organisms growing on the nets in Norway

**Gammarids** 



**Caprellina** 



Tubularia larynx
•Common flowerhead


Mytilus edulis

Nematoda

**Round worms** 



# Stomach content analysis Goldsinny 2002



## Hides

- The netpen environment is rather artificial for the cleanerfish
- We help the cleanerfish we offer alternative places for hiding















